

Premium solvent based corrosion preventive compound

Tectyl™ 502-C is a solvent cutback, soft wax base, corrosion preventive compound.

Tectyl™ 502-C is designed to protect the insides of gearboxes, without removal after installation.

Tectyl™ 502-C is designed to protect parts in indoor and covered storage and shipment.

Tectyl™ 502-C is designed to protect ferrous and non-ferrous parts for indoor or covered storage and during shipment.

Tectyl™ 502-C cures to a dark amber, transparent, soft greasy film.

Approvals / Performance Levels

Tectyl™ 502-C	
Recommended Dry Film Thickness over metal profile	50 µm
Salt Spray Salt Spray; 5 % NaCl @ 35°C; ISO 9227 NSS (Q-Panels, Type R, ASTM A1008)	min. 7 days
Humidity Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH (Q-Panels, Type R, ASTM A1008)	min. 40 days
MIL-C-16173E Military Specification	Grade 2 Class 2
Protection indoor	min. 24 months
Protection outdoor	min. 6 months

Applications

Surface Preparation

The maximum performance of **Tectyl™ 502-C** cutbacks can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. CorPro recommends that the metal substrate temperature is 10-35 °C at the time of product application. Direct contact of **Tectyl™ 502-C** with PVC can cause compatibility problems. Please test prior to use.

Application

Tectyl™ 502-C is formulated to be used as supplied. CorPro recommends that the ambient and product temperature be 10-35 °C at the time of product application. Do not thin **Tectyl™ 502-C**. Incorrect thinning will affect film build, dry time and product performance. **Tectyl™ 502-C** can be applied by low pressure air spray or dipping. Details on application can be found in the application chart.

Removal

Tectyl™ 502-C can in the wet phase be removed with **Tectyl™ Biocleaner**, **Tectyl™ 150** or low-pressure steam. If dried and cured the film of **Tectyl™ 502-C** can be removed with **Tectyl™ Biocleaner** or **Tectyl™ 150**. When applied in a gearbox or similar application, **Tectyl™ 502-C** does not need to be removed and will dissolve in the oil.

Features & Benefits

Superior Protection

At the recommended DFT **Tectyl™ 502-C** will protect against corrosion during storage, domestic and overseas transport.

Processing

Tectyl™ 502-C is easy to apply and easy to remove, when no longer needed.

Economical

With a DFT of only 50 microns, **Tectyl™ 502-C** can protect a big surface with just little amount of the product.

Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit www.tectyleurope.com.

Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office.

Protect the environment

Comply with local regulations. Do not discharge into drains, soil or water.

Typical Properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

Tectyl™ 502-C	
Flash point	40°C PMCC
Density @ 20°C	0.88 kg/ltr
Theoretical coverage @ Recommended dry film thickness	22.2 sqm/ltr
Viscosity (DIN 53211) Cup No. 4 @ 20°C (at time of manufacture)	16 sec
Non volatile weight	61%
Cure Time @ 20°C	24 hours
Storage temperature	10 - 35°C
VOC Content ISO 11890-2 (10.4)	317 g/ltr

Storage

Tectyl™ 502-C should be stored at temperatures between 10-35 °C. Do not freeze **Tectyl™ 502-C**. Mild agitation is recommended prior to use. Due to its composition **Tectyl™ 502-C** can be subject to postproduction viscosity changes during storage. Under proper storage conditions **Tectyl™ 502-C** is best before 36 months after production date.

Caution

Adequate ventilation is required for cure and to ensure against formation of combustible liquid. the partially cured film should not be exposed to ignition sources such as flares, flames, sparks, excessive heat or torches. refer to the safety data sheet for additional handling and first aid information.

Note

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Performance level section. If a primer, other than a CorPro recommended product is required, written authorization must be obtained from CorPro.

State of the information

March 10, 2025

Validity

This information only applies to products manufactured in the following regions: Europe



<https://cp.qrto.me/p/15>



<https://tectyleurope.com>