

## Premium water based, fast drying, corrosion preventative compound

**Tectyl™ 3217 E** has been specially designed for use as an environmentally friendly protector of unfinished metal and industrial finishes. The dry film is tack free and prevents dust build up.

**Tectyl™ 3217 E** is excellent for use on aluminum and galvanized surfaces as protector. Eliminates water spotting caused by acidic rain or hard water.

**Tectyl™ 3217 E** cures to a transparent, resilient, firm film.

### Approvals / Performance Levels

Tectyl™ 3217 E	
<b>Recommended Dry Film Thickness</b> over metal profile	50 µm
<b>Weathering resistance</b> PASS (ISO 4892-3)	min. 1,000 hours
<b>Salt Spray</b> Salt Spray; 5 % NaCl @ 35°C; ISO 9227 NSS (Q-Panels, Type R, ASTM A1008)	min. 21 days
<b>Humidity</b> Humidity; 100 % RH; @ 40°C; ISO 6270-2 CH (Q-Panels, Type R, ASTM A1008)	min. 100 days
<b>Protection indoor</b>	min. 36 months
<b>Protection outdoor</b>	min. 12 months

### Applications

#### Surface Preparation

The maximum performance of **Tectyl™ 3217 E** can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale. CorPro recommends a substrate temperature of 10-35 °C at the time of product application.

#### Application

**Tectyl™ 3217 E** is formulated to be used as supplied. CorPro recommends that the ambient and product temperature be 10-35 °C at the time of product application. Always ensure uniform consistency prior to use. Avoid contamination with other products in pumps and lines. CorPro recommends that the ambient and product temperature be 10-35 °C at the time of product application. For application **Tectyl™ 3217 E** CorPro recommends a low pressure airspray application or airless application with a small airless nozzle. Details on application can be found in the application chart.

#### Removal

**Tectyl™ 3217 E** is not intended for removal. In the wet phase **Tectyl™ 3217 E** can be removed with water or with **Tectyl™ Biocleaner**. If dried and cured **Tectyl™ 3217 E** can be removed with ethyl acetate.

### Features & Benefits

#### Superior protection

**Tectyl™ 3217 E** is an excellent preservative for the storage or transit protection of finished and unfinished automotive parts.

#### Environment

**Tectyl™ 3217 E** is a water-based product with low VOC content.

#### Easy application

Due to the viscosity **Tectyl™ 3217 E** is easy to apply and forms excellent film formation at suitable layer thickness for highest efficiency.

#### Fast drying

With a dry to touch time of 30-60 minutes and a cure time of 8 hours **Tectyl™ 3217 E** is a fast-drying protective coating.

### Trusted since 1930

Since 1930, Tectyl™ protective coatings have been extending the operational life of cars, trucks, buses and other vehicles and equipment. The Tectyl name is synonymous with quality coatings that are easy to apply, long-lasting and easy to remove when no longer required.

For more information on Tectyl products, programs and services please visit [www.tectyleurope.com](http://www.tectyleurope.com).

### Health & Safety

This product is not likely to present any significant health or safety hazards when properly used in the recommended application and good standards of personal hygiene are maintained. Reference is made to the Safety Data Sheet (SDS) which is available on request via your local sales office.

### Protect the environment

Comply with local regulations. Do not discharge into drains, soil or water.

## Typical Properties

Typical property characteristics are based on current production. Whilst future production will conform to Tectyl specifications, variations in these characteristics may occur.

Tectyl™ 3217 E	
Flash point	not applicable
Density @ 20°C	1.02 kg/ltr
Theoretical coverage @ Recommended dry film thickness	10.4 sqm/ltr
Viscosity (Brookfield @ 20°C) @ 2 RPM	760 mPa·s (cP)
Viscosity (Brookfield @ 20°C) @ 20 RPM	700 mPa·s (cP)
Viscosity (Zahn) Zahn Cup No. 3 @ 20°C	78 sec
Viscosity (DIN 53211) Cup No. 4 @ 20°C (at time of manufacture)	131 sec
Non volatile weight	28%
Dry to Touch @ 20°C	min. 1 hour
pH @ 20°C	9.7
Cure Time @ 20°C	8 hours
Storage temperature	10 - 35°C
VOC Content ISO 11890-2 (10.4)	118 g/ltr

## Storage

**Tectyl™ 3217 E** should be stored at temperatures between 10-35 °C. Do not freeze **Tectyl™ 3217 E**. Mild agitation is recommended prior to use. Due to its composition **Tectyl™ 3217 E** can be subject to postproduction viscosity changes during storage. Under proper storage conditions **Tectyl™ 3217 E** is best before 12 months after production date.

## Caution

Refer to the Safety Data Sheet for additional handling and first aid information.

## Note

The addition of any product over or under this coating is not recommended. The use of additional coatings could result in chemical incompatibility, thus affecting the performance of this coating as stated in the Performance level section. If a primer, other than a CorPro recommended product is required, written authorization must be obtained from CorPro.

## State of the information

September 30, 2025

## Validity

This information only applies to products manufactured in the following regions: Europe



<https://cp.qrto.me/p/27>



<https://tectyleurope.com>